



www.thistlebond.com

# TECHNICAL DATA SHEET

## Hycote I62

**ThistleBond 'Hycote I62'** is a high performance solvent free coating designed for aggressive environments.

**ThistleBond 'Hycote I62'** is based on a special liquid epoxy polymer reacted with a blend of amine and polyamino resins reinforced with inert pigments and silicas which produces a system with exceptional chemical and corrosion resistance.

**ThistleBond 'Hycote I62'** offers excellent adhesion to steel and concrete and has outstanding abrasion and erosion resistance making it ideal for tanks, containment areas, steelwork and floors.

**Before proceeding, please read the following information carefully to ensure that the correct application procedure is fully understood.**

### SURFACE PREPARATION

**Steel Surfaces** - All surfaces to be coated should be abrasive blast cleaned to a minimum Sa2½ in accordance with BS7079 Part A1:1989 or equivalent with a blast profile corresponding to 'Medium' in accordance with BS7079 Part C3 / ISO 8503 / 1. All loose abrasive dust and debris must be blown clear or vacuum cleaned away. Steel surfaces do not require priming but should be coated within 4 hours of blast cleaning to prevent rash rusting.

**Concrete Surfaces** - All concrete to be coated should either be lightly abrasive blast cleaned using wet or dry abrasive techniques or alternatively high pressure water jetting. Care must be taken not to expose the aggregate in the concrete. All dust and abrasive material shall be removed from the surface prior to coating.

Concrete surfaces should have a maximum content of 7% prior to any coating being applied.

Concrete surfaces should be primed with either **ThistleBond 'Low Viscosity MP Primer'** or **ThistleBond 'MA3 Tie-Coat'** in accordance with the product tech sheet.

### MIXING

**ThistleBond 'Hycote I62'** is a two component material comprising resin and hardener components which must be mixed together prior to use.

Stir the contents of the resin component, continue stirring and gradually add the total contents of the hardener container, stir the combined mix until completely homogeneous.

The mixed materials should be used within 45 minutes of mixing at 20°C (68°F). This time will be reduced at higher temperatures and extended at lower temperatures.

### APPLICATION

Application should not be carried out at temperatures below 5°C nor when relative humidity exceeds 85% or when the surface to be coated is less than 3°C above the dew point.

**ThistleBond 'Hycote I62'** is suitable for application by brush or roller, using good quality brushes or short to medium pile rollers.

On concrete surfaces it is important to stipple the **ThistleBond 'Hycote I62'** into the primed surface to ensure good wetting of the surface.

For large applications **ThistleBond 'Hycote I62'** can be applied by dual feed hot airless spray equipment, full technical details can be supplied on request from the **Technical Centre**.

In areas requiring a slip deterrent finish, **ThistleBond H.D.** or **W.D. Grip** should be incorporated into the first coat of a two coat system.

All equipment should be cleaned IMMEDIATELY after use with **ThistleBond 'Cleaner'**.

**Theoretical Coverage Rate**4 m<sup>2</sup>/litre at 250 microns dft (43 ft<sup>2</sup>/litre at 10 mils dft)**Recommended Film Thickness**

Wet 250 microns (10 mils)

Dry 250 microns (10 mils)

**PHYSICAL CONSTANTS****Mixing Ratio** 2 parts resin to 1 part hardener by volume**Appearance** Resin Viscous coloured liquid  
Hardener Clear Amber liquid**Drying & Cure**

<b>Times at 20°C</b>	Usable Life	45 minutes
	Touch Dry	6 hours
	Minimum Overcoating	6 hours
	Maximum Overcoating	48 hours
	Full Cure	7 days

**Volume Solids** 100%**V.O.C.** Nil**Shelf Life** Use within 5 years of purchase. Store in original sealed containers at temperatures between 5°C (40°F) and 30°C (86°F).**Food Contact** Meets USDA requirements for incidental food contact.  
  
Meets FDA CFR 21.175.300 requirements for food contact.**PHYSICAL PROPERTIES**

<b>Abrasion Resistance</b>	40 mgm loss per 1000 cycles -
ASTM D 4060	1 kg load - CS17 wheel
<b>Impact Resistance</b>	2.6 joules (23 in/lbs)
ASTM G14	
<b>Dry Heat Resistance</b>	100°C (212°F)
ASTM D248	
<b>Water Vapour Permeability</b>	1.2 gm.mm/m <sup>2</sup> /24hrs
ASTM D1653	
<b>Salt Fog Resistance</b>	Excellent, unaffected after
ASTM B117	10,000 hrs exposure
<b>Humidity Resistance</b>	Unaffected 5,000 hrs exposure
BS 3900 Part F2	
<b>Direct Pull Adhesion</b>	63 kg/cm <sup>2</sup> (900 psi)
ASTM D4541	

**HEALTH AND SAFETY**As long as normal good practice is observed **ThistleBond 'Hycote 162'** can be safely used.

Protective gloves should be worn.

Vapour masks should be worn for spray application.

A fully detailed **Material Safety Data Sheet** is either included with the material or is available on request.**PACKAGING**

Supplied in 5 litre packs

The information provided in this Product Data Sheet is intended as a general guide only and should not be used for specification purposes. The information is given in good faith but we assume no responsibility for the use made of the product or this information because this is outside the control of the company. Users should determine the suitability of the product for their own particular purposes by their own tests. Detailed specifications are available on request from the company.

FOR FURTHER INFORMATION PLEASE CONTACT



[www.thortex.co.uk](http://www.thortex.co.uk)  
Thortex Division of E. Wood Ltd.

Standard Way, Northallerton, N. Yorks. U.K. DL6 2XA  
Tel: +44(0)1609 780170 Fax: +44(0)1609 780438 & 777905  
E Mail: [thortex@ewood.co.uk](mailto:thortex@ewood.co.uk)  
Buy online: [www.thortex.co.uk/shop](http://www.thortex.co.uk/shop)