



www.thistlebond.com

TECHNICAL DATA SHEET

Hycote 175

ThistleBond 'Hycote 175' is a high performance solvent free coating designed for use where exceptional resistance to chemical attack is required.

ThistleBond 'Hycote 175' is based on a special Phenolic epoxy resin and a polyamine curing agent system which produces a highly cross linked polymer network. This unique system prevents permeation and subsequent attack of the coating by highly aggressive chemicals, allowing the system to be used whenever superior chemical resistance is required.

ThistleBond 'Hycote 175' offers excellent adhesion to steel and concrete, has outstanding resistance to a wide range of industrial chemicals even under total immersion conditions and is ideal for tanks, pipework, containment dykes, bund areas, desulphurisation units etc.

Before proceeding, please read the following information carefully to ensure that the correct application procedure is fully understood.

SURFACE PREPARATION

Steel Surfaces - All surfaces to be coated should be abrasive blast cleaned to a minimum Sa2½ in accordance with BS7079 Part A1:1989 or equivalent with a blast profile corresponding to 'Medium' in accordance with BS7079 Part C3 / ISO 8503 / 1. All loose abrasive dust and debris must be blown clear or vacuum cleaned away. Steel surfaces do not require priming but should be coated within 4 hours of blast cleaning to prevent rash rusting.

Concrete Surfaces - All concrete to be coated should either be lightly abrasive blast cleaned using wet or dry abrasive techniques or alternatively high pressure water jetting. Care must be taken not to expose the aggregate in the concrete. All dust and abrasive material shall be removed from the surface prior to coating.

Concrete surfaces should have a moisture content of 7% prior to any coating being applied.

Concrete surfaces should be primed with either **ThistleBond 'Low Viscosity MP Primer'** or **ThistleBond 'MA3 Tie-Coat'** in accordance with the product tech sheet.

MIXING

ThistleBond 'Hycote 175' is a two component material comprising resin and hardener components which must be mixed together prior to use.

Stir the contents of the resin component, continue stirring and gradually add the total contents of the hardener container, stir the combined mix until completely homogeneous.

The mixed materials should be used within 30 minutes of mixing at 20°C (68°F). This time will be reduced at higher temperatures and extended at lower temperatures.

APPLICATION

Application should not be carried out at temperatures below 5°C nor when relative humidity exceeds 85% or when the surface to be coated is less than 3°C below the dew point.

Best application results are obtained at a minimum substrate and product temperature of 20°C. For optimum chemical resistance, the system must be applied and cured at a minimum temperature of 20°C for at least 7 days prior to return to service.

ThistleBond 'Hycote 175' is suitable for application by brush or roller, using good quality brushes or short to medium pile rollers.

On concrete surfaces it is important to stipple the **ThistleBond 'Hycote 175'** into the primed surface to ensure good wetting of the surface.

For large applications **ThistleBond 'Hycote 175'** can be applied by dual feed hot airless spray equipment, full technical details can be supplied on request from the **ThistleBond Technical Centre**.

All equipment should be cleaned IMMEDIATELY after use with **ThistleBond 'Cleaner'**.

Theoretical Coverage Rate

2.9 m²/kg at 300 microns dft (31 ft²/litre at 12 mils dft)

Recommended Film Thickness

Wet 300 microns (12 mils)

Dry 300 microns (12 mils)

PHYSICAL CONSTANTS

Mixing Ratio 2 parts resin to 1 part hardener by volume

Appearance Resin Viscous coloured liquid
Hardener Clear Amber liquid

Drying & Cure Times

at 20°C (68°F)	Usable Life	30 minutes
	Initial Set	4½ hours
	Minimum Overcoating	4½ hours
	Maximum Overcoating	24 hours
	Full Cure	7 days

Volume Solids 100%

V.O.C. Nil

Shelf Life Use within 5 years of purchase. Store in original sealed containers at temperatures between 5°C (40°F) and 30°C (86°F).

Food Contact Meets USDA requirements for incidental food contact.

Chemical Resistance (At 20°C)

Unaffected by total immersion in:-
Acetic Acid up to 20%
Hydrochloric Acid up to 35%
Ortho Phosphoric Acid up to 75%
Sulphuric Acid up to 98%
Nitric Acid up to 30%
Sodium Hydroxide All Concentrations

PHYSICAL PROPERTIES

Abrasion Resistance 60 mgm loss per 1000 cycles
ASTM D 4060 -1 kg load-CS17 wheel

Impact Resistance 2.2 joules (19½ in/lbs)
ASTM G14

Dry Heat Resistance 177°C (350°F)
ASTM D248

Water Vapour Permeability 4.69 x 10⁻⁶ perm.cm
ASTM D1653

Salt Fog Resistance Excellent, unaffected after
ASTM B117 10,000 hrs exposure

Humidity Resistance Unaffected 5,000 hrs exposure
BS 3900 Part F2

HEALTH AND SAFETY

As long as normal good practice is observed **ThistleBond 'Hycote 175'** can be safely used.

Protective gloves should be worn.

Vapour masks should be worn for spray application.

A fully detailed **Material Safety Data Sheet** is either included with the material or is available on request.

PACKAGING

Supplied in 5 kg packs

The information provided in this Product Data Sheet is intended as a general guide only and should not be used for specification purposes. The information is given in good faith but we assume no responsibility for the use made of the product or this information because this is outside the control of the company. Users should determine the suitability of the product for their own particular purposes by their own tests. Detailed specifications are available on request from the company.

FOR FURTHER INFORMATION PLEASE CONTACT



www.thortex.co.uk

Thortex Division of E. Wood Ltd.

Standard Way, Northallerton, N. Yorks. U.K. DL6 2XA

Tel: +44(0)1609 780170 Fax: +44(0)1609 780438 & 777905

E Mail: thortex@ewood.co.uk

Buy online: www.thortex.co.uk/shop